Certified Companies

Date of issue : 05/01/2005
Last. mod. date : 17/07/2008

**Product code**

## 02033 RI-205/80 GLOSS CLEAR AP 900

**Description**

Gloss clear plasticised vinyl film, with good flexibility and conformability on curved surfaces.

Printing methods: solvent and UV screenprinting, offset UV, hot stamping.

Permanent adhesive with very good adhesion on glass and on a wide variety of substrates, except for apolar (PE, PP).

BGVV compliance (indirect food contact).Promotional labels, window stickers, electrowelded pouches. On request this product is available on a split -back backing (RI-LINE).

**FACE MATERIAL**

| | |
|---|---|
| Type | Plasticised vinyl film |
| Colour and Finish | Clear, Gloss |
| Weight | 104 g/m² |
| Thickness | 80 µ |

**ADHESIVE**

| | |
|---|---|
| Reference | AP 900 |
| Type | Acrylic permanent |
| Min. Appl. Temp. | +10°C |
| Service Temp. | -30°C/+120°C |
| Shear | Very High |
| Tack FTM9 | 6 N/inch² |
| FinAdh FTM2 | 9 N/inch |

**RELEASE BACKING**

| | |
|---|---|
| Type | 1 side clay-coat |
| Colour and Finish | White |
| Weight | 135 g/m² |
| Thickness | 150 µ |

**CHEMICAL RESISTANCE**

| | |
|---|---|
| Detergent | No effect (24 Hrs) |
| Gasoline | No effect (1 Hrs) |
| SAE20 Motoroil | No effect (24 Hrs) |
| 10% HCl | No effect (10 min) |
| 10% NH4OH | No effect (10 min) |

**Storage**

The material must be stored at a temperature of 22°C +/- 2°C and 50% +/- 5% of Relative Humidity. Do not expose to direct sun light.
The area must be dry and clean. Please keep the material in the original packaging when not used in order to protect it from dust and contaminations.
All values presented in this data sheet are typical. Ritrama's data sheets provide only the general characteristics of the Product. It is the responsibility of the Customer and/or End User to determine that the Product is fit for the purpose for which the Customer and/or End User wish to use it. Ritrama can give no guarantee beyond the information given in the data sheet.


| | | |
|---|---|---|
| Ritrama S.p.A. | Tel. +39 02 955 459 1 | info@ritrama.it |
| Ritrama S.p.A. Sassoferrato | Tel. +39 0732 97061 | info@ritrama.it |
| Coating Ricofin S.r.l. | Tel. +39 02 955 430 1 | info@ricofin.it |
| Ritrama S.A. | Tel. +34 93 729 49 98 | ritrama@ritrama.es |
| Ritrama Ltd.(UK) | Tel. +44 161 786 1760 | sales@ritrama.co.uk |
| Ritrama Inc. Minneapolis (USA) | Tel. +1 612 378 2277 | info@ritrama.com |
| Ritrama Inc. Cleveland (USA) | Tel. +1 216 851 2300 | info@ritrama.com |


edp European Digital Press Awards 2008
RITRAMA WINNER
OF THE BEST WIDE FORMAT SELF-ADHESIVE FILM