

## Product information

IMPEX® Clear Polycarbonate is a virtually unbreakable material. Both sides have a co-extruded UV protection layer which gives it superb weather resistance, making it ideal for both indoor and outdoor use. It also has a very good fire performance for thicknesses from 1.5 up to 6mm according to EN 13501-1.

It's easy to fabricate and gives an exceptional performance at both low and high temperatures (from -40°C to +135°C).

### Application

Sign and displays • Lettering • Partitions • Safety glazing and guards

### Print suitability

Screen Print • UV

### Conversion suitability

Saw • Punching • Glueing • Drilling • Thermoforming • Engraving • Vacuum forming • Line bending

## Stock schedule

| Sizes           | Calliper |     |     |     |     |     |     |      |      |
|-----------------|----------|-----|-----|-----|-----|-----|-----|------|------|
|                 | 1mm      | 2mm | 3mm | 4mm | 5mm | 6mm | 8mm | 10mm | 12mm |
| 3050mm x 2050mm |          | ●   | ●   | ●   | ●   | ●   | ●   | ●    | ●    |
| 2050mm x 1250mm | ●        |     |     |     |     |     |     |      |      |

● UVP ● Non UVP

## Specification

### General

|                                                              |               |
|--------------------------------------------------------------|---------------|
| Density ISO 1183 (kg/m <sup>3</sup> )                        | 1200          |
| Moisture absorption (23°C saturation in water) ISO 62-1 (%)  | 0.12          |
| Biocompatibility (skin contact) ISO 10993-5 (Classification) | Not cytotoxic |

### Mechanical

|                                                                         |      |
|-------------------------------------------------------------------------|------|
| Tensile modulus ISO 527-2 (MPa)                                         | 2200 |
| Tensile strength ISO 527-2 (MPa)                                        | 60   |
| Elongation ISO 527-2 (%)                                                | 80   |
| Tensile modulus ISO 527-2 (MPa)                                         | 2200 |
| Tensile strength ISO 527-2 (MPa)                                        | 60   |
| Elongation ISO 527-2 (%)                                                | 80   |
| Flexural modulus ISO 178 (MPa)                                          | 2000 |
| Flexural strength ISO 178 (MPa)                                         | >90  |
| Impact strength – Charpy (unnotched) ISO 179-1/1eU (kJ/m <sup>2</sup> ) | NB   |
| Impact strength – Charpy (notched) ISO 179-1/1eA (kJ/m <sup>2</sup> )   | >13  |
| Impact strength – Izod (notched) ISO 180 (kJ/m <sup>2</sup> )           | >10  |
| Ball indentation Hardness H 358/30 ISO 2039-1 (MPa)                     | 110  |

This information is given for general guidance only and is subject to change without notice.

## Optical

|                                                      |       |
|------------------------------------------------------|-------|
| Light transmission (3mm) ISO 13468-1 (%)             | 86    |
| Refractive Index ISO 489 (nD20)                      | 1.585 |
| Solar energy transmittance, g value (3mm) EN 410 (%) | 81    |

## Thermal

|                                                                           |          |
|---------------------------------------------------------------------------|----------|
| Heat deflection temperature (method A) ISO 75-2 (°C)                      | 135      |
| Vicat Temperature (method B 50) ISO 306 (°C)                              | 145      |
| Coefficient of linear expansion ISO 11359-1, -2 (mm/m*K)                  | 0.065    |
| Max. service temperature continuous use (°C)                              | 115      |
| Max service temperature short term use (°C)                               | 135      |
| Degradation temperature (°C)                                              | >280     |
| Forming temperature (°C)                                                  | 180-210  |
| Specific heat capacity ISO 11357-4 (J/gK)                                 | 1.17     |
| Thermal conductivity Iso 22007-1 (W/mK)                                   | 0.2      |
| Fire performance (1.5-6mm, clear transparent) EN 13501-1 (Classification) | B-s1, d0 |

## Electrical

|                                         |                      |
|-----------------------------------------|----------------------|
| Dielectric strength IEC 60243-1 (kV/mm) | >30                  |
| Volume resistivity IEC 62631-3-1 (Ω.m)  | 1015                 |
| Surface resistivity IEC 62631-3-2 (Ω)   | 1015                 |
| Dielectric constant (50Hz) IEC 60250    | 3.0                  |
| Dissipation factor (50Hz) IEC 60250     | 8 x 10 <sup>-4</sup> |

## Credentials



The CO<sub>2</sub> emissions from this product can be mitigated through the Carbon Capture® programme, directly supporting the work of the Woodland Trust.

Technical information is given as an indication of typical values and is not to be considered as a commitment by the manufacturers.